AB-SCHOMBURG YAPI KİMYASALLARI A.Ş.

19 Mayıs Mah. Turapoğlu Sok. Hamdiye Yazgan İş Merk. No.4/8 34736 KOZYATAĞI - İSTANBUL

Tel : +90-216-302 71 31/-32
Fax : +90-216-302 70 01
e-mail : info@ab-schomburg.com.tr
Web : www.ab-schomburg.com.tr
Web : www.schomburg.com





Technical Data Sheet

TEYAPLAST-2K

Two component cement based semi-elastic waterproofing material

Description:

Semi-elastic, cement based waterproofing slurry which is effective to both negative and positive water pressure.

Areas of Application:

TEYAPLAST-2K can be used to waterproof,

- Water tanks (suitable for potable water tanks, no toxic effect.),
- Pools,
- Terraces and balconies,
- Wet areas such as baths, toilets, kitchens and laundries,
- Concrete faces of buildings,
- Basements from both negative and positive sides,
- Retaining walls.

Properties/Advantages:

- Water tight up to 20 m. water column,
- Perfect adhesion to concrete surfaces,
- Crack bridging,
- Suitable to use with reinforcement mash,
- High impact resistance,
- Application without joints is possible.

Technical Data:

Basis: cement based slurry

Color: grey

Density: 1,8 kg/liter

Pot life: 30 minutes after mixing

Flexural strength: 80 kg/cm² Compressive strength: 250 kg/cm² Adhesion strength: 25 kg/cm²

Elasticity modulus: 30.000 kg/cm² (x10 more

elastic than the concrete.)

Water tight up to: with 4 kg/m² consumption

constituting 2 mm. thickness up to 20 m. water column.

Application/surface

temperature: $+8^{\circ}\text{C} - 30^{\circ}\text{C}$

Curing time: 7 days at 20°C - 23°C

Packaging:

25 kg. set. (19 kg. powder + 6 kg. liquid component.)

Storage:

The product can be kept for 6 months in a dry condition.

Surface Preparation:

All loose particles and particles which can prevent adhesion must be removed from the surface. ASOCRET-130 and ASOCRET-105 repair mortar shall be used to repair irregularities if needed.

Product Preparation:

- Mix the two components in a clean pail.
- If needed, with respect to weather and application conditions, water can be mixed into the slurry with a maximum ratio of 10%.

Method of Application:

- Application can be done by a trowel or a brush.
- The thickness of the material varies between 1-2 mm. according to the water pressure.
- For water pressures between 1-5 m. water column the consumption is 3 kg/m².
- If the application will be done for negative pressure, prime the surface with water mixed EMÜLFIX with portions of 1:4.

Consumption:

Wet rooms: 3 kg/m² in two layers

Water tanks, pools and terraces: 3,5-4,0 kg/m²

in two layers

Cleaning:

Clean the tools right after the application.

Important Advices:

- For risky and special applications please ask our assistance.
- Do not apply on the terraces when the weather is too hot or surface is under direct sun light.

Health and Safety:

Refer to MSDS.